

PRODUCT INFORMATION

Level of use	23 - 31 Heavy Domestic Use	EN ISO 10874
Total thickness	4.2mm	RN ISO 24346
Wear layer	0.3mm	EN ISO 24340
Wear layer PUR treatment	Superguard®	
Total weight g/m²	7.275	EN ISO 23997
Installation method	L2C angle-drop click & roller	
Recommended underlay	xtrafloor® silent for click LVT	
Warranty for residential use	15 years	
Warranty for commercial use	5 years	

SIZE & PACKAGING

VIVO I WOOD planks	19.1 x 131.6cm 7.52 x 51.81"	EN ISO 24342
VIVO I STONE tiles	30.06 x 60.46cm 11.83 x 23.8"	EN ISO 24342
Box of VIVO I WOOD planks	2.01m²/box 21.65ft²/box	8pcs/box
Box of VIVO I STONE tiles	2m²/box 21.52ft²/box	11pcs/box

TEST RESULTS

Inflammability	Bfl-S1	EN 13501
Scratch resistance	Class T	EN 660-2
Squareness & straightness	≤0.35mm	EN ISO 24342
Slip resistance	DS	EN 12893
Slip restraint	R10	DIN 51130
Residual indentation	≤0.10mm	EN ISO 24343-1
Furniture leg resistance	No cracks, no damage	EN ISO 16581
Curling	≤2mm	EN ISO 23999
Electrical resistance	≤10⁰0hm	EN 1081
Dimensional stability	Norm: ≤0.25% Average result measured: ≤0.05%	EN ISO 23999
Heat insulation	0.25w/(m.K)	EN 12524
Thermal Resistance	0.0154m².K/W	EN ISO 12664
Electrostatic performance	<2kV	EN 1815
Formaldehyde group	E1	EN 717-1
Acoustic insulation	4dB	EN ISO 717-2
Acoustic insulation with xtrafloor® silent underlay	19dB	EN ISO 717-2
Stain resistance	Very good	EN ISO 26987
Light fastness	≥6	ISO 105-B02
Underfloor heating	Suitable, max 27°C	EN 12524

Warranty

The warranty covers manufacturing defects and premature wear in the event of normal use. If installing VIVO with underlay, xtrafloor® silent acoustic underlay must be used to fulfil the terms of your warranty. Use of another underlay may cause the floor to fail and will void your warranty.

Photography

The photography in this brochure are for illustrative purposes only and do not represent accurate colour. Please order samples of your preferred VIVO floor before making your decision.

